Type MLSG – Slimpack™, 5000 hr@125 °C, Aluminum Electrolytic



With a profile of 1.0" by 0.5" type MLSG Slimpack[™] capacitors fit into the tightest of spaces and meets a DC test of 5000 hrs at rated voltage, 125 °C. MLSG SlimpackTM is a perfect fit for military and aerospace applications requiring a low profile, rugged design and long-life. Specify type HRMLSG for high reliability burn-in.

Highlights

- 5000 hrs @ rated voltage, 125 °C
- Stainless steel case
- Withstands more than 80,000 feet altitude
- 80 g vibration
- Type HR, high reliability burn-in

pecifications												
Temperature Range	−55 °C to +125 °C											
Rated Voltage Range	10 Vdc to 250 Vdc											
Capacitance Range	140 μF to 24,000 μF											
Capacitance Tolerance	±20%											
Leakage Current	\leq 0.002 CV $\mu A,$ @ 25 °C and 5 mins.											
Ripple Current Multipliers	Case Temperature											
	45 °C	55	°C	65 °C	75 °C	85 °	C 9	5 °C	105 °C	115 °C	125 °C	
	1.41	1.3	32	1.22	1.12	1.0	0 0	.87	0.71	0.50	0.00	
	Ambient Temperature, No Heatsink											
	45 °C	55	s°C	65 °C	75	°C 8	35 °C	95 °C	105	°C 115	°C 125 °	
	0.63		.58	0.54	0.4	9	0.44	0.38	0.3	I 0.2	2 0.00	
	Frequency											
			50 H	lz 60	Hz 1	20 Hz	360	Hz 1	kHz	5 kHz	10 kHz & up	
	5 to 4	0 V	0.95	5 0.9	96	1.00	1.0	3	1.04	1.04	1.04	
	60 to 2	50 V	0.80	0.8	84	1.00	1.1	8	1.25	1.30	1.30	
Low Temperature Characteristics	Impedance ratio: $Z_{-55 ^{\circ}C} / Z_{+25 ^{\circ}C} @ 120 \text{Hz}$ $\leq 10 (5 - 20 \text{Vdc})$ $\leq 2 (25 - 250 \text{Vdc})$											
DC Life Test	5000 h at rated voltage @ 125 °C Δ Capacitance +/- 15% less than or equal to 60 Vdc Δ Capacitance +/- 10% greater than 60 Vdc ESR 200% of limit DCL 100% of limit											
Shelf Life Test	500 h @ 125 °C Capacitance 100% of limit ESR 100% of limit DCL 100% of limit											
Vibration Mounting: Vibration capability is dependent upon mounting restraint.	MIL-STD-202, Meth. 204, Sine Swept. IEC 60068-2-6 JK Case = 80g All Others = 50g											


Specifications

Type MLSG – Slimpack™, 5000 hr@125 °C, Aluminum Electrolytic

	Large Sides	 Level The specimens, while deenergized or operating under the load conditions specified, shall be subjected to the vibration amplitude, frequency range, and duration specified for each case size. Amplitude The specimens shall be subjected to a simple harmonic motion having an amplitude of either 0.06-inch double amplitude (maximum total excursion) or peak level specified above (XXg peak), whichever is less. The tolerance on vibration amplitude shall be ±10 percent. Frequency Range The vibration frequency shall be varied logarithmically between the approximate limits of 10 to 2,000 Hz. Sweep Time and Duration The entire frequency range of 10 to 2,000 Hz and return to 10 Hz shall be traversed in 20 minutes. This cycle shall be performed 12 times in each of three mutually perpendicular directions (total of 36 times), so that the motion shall be applied for a total period of approximately 12 hours. Interruptions are permitted provided the requirements for rate of change and test duration are met. Established Reliability capacitors shall be subjected to a minimum of 100 percent of the dc rated voltage at 85 °C for 48 hours minimum but not to exceed 96 hours. During this test, capacitors shall be adequately protected against temporary voltage surges of 10 percent or more of the test voltage. After burn-in, the capacitors shall be returned to room ambient conditions and the dc leakage, capacitance, and ESR shall be measured with respect to specified limits. 								
	Large Staes									
ESL <	Heatsinked	Insulation	°C/W	°C/W	°C/W	°C/W				
ESL <3		None	6.6	4.8	3.8	3.1				
ESL <	one	Polyester	7.2	5.3	4.2	3.4				
ESL st	h a th	None	4.4	3.1	2.4	2				
ESL st	both	Polyester	4.7	3.3	2.6	2.2				
	≤30 nH measured 1/4" from case at 1 MHz									
Ca	Case JK = 30 Case JA = 39 Case JH = 48 Case JB = 57									
Terminals - lead free version available 18	18 AWG copper wire with 60/40 tin-lead electroplate, 20 amps max									
Case Material St	Stainless Steel									
	The ripple current capability is set by the maximum permissible internal core temperature, 125 °C.									
Fc	The ripple currents in the ratings tables are for 85 °C case temperatures. For air temperatures without a heatsink use the multipliers Ambient Temperature, No Heatsink.									
Heatsink Cooled Te	Temperature rise from the internal hottest spot, the core, to ambient air is									
	$\Delta T = I^2(ESR)(\theta cc + \theta ca)$, recommended max ΔT of 30 °C									
ar	where θ cc is the thermal resistance from core to case and θ ca from case to ambient. To calculate maximum ripple capability with the MLS attached to a heatsink use the maximum core temperature and the values for θ cc.									
in re th po	As an illustration, suppose you operate an insulated MLSG262M060JB0C in 95 °C air and attach it to a commercial heatsink with a free-air thermal resistance of 2.7 °C/W. Use a good thermal grease between the MLS and the heatsink, and the total thermal resistance is 2.7 +3. 4 or 6.1° C/W. The power which would heat the core to 125 °C is (125 - 95)/6. 1 or 4.9 W. For ar ESR of 47 m Ω , 4.9 W equates to a ripple current of 10.2 A.									


Type MLSG – Slimpack[™], 5000 hr@125 °C, Aluminum Electrolytic

Part Numbering System



Outline Drawing

Note: The polyester tape wrap may add up to 0.020 inches to the thickness and width of the capacitor.



Type MLSG – Slimpack[™], 5000 hr@125 °C, Aluminum Electrolytic

Ratings


	Сар	Part Number	Ω 120 Hz 25 °C Cat. ESR	Ω 10 KHz 25 °C Cat. ESR	Ripple (A) Case @ 85°C 120Hz	Ripple (A) Case @ 85°C 10kHz	Surge 25 °C Vdc	Case Length	105 °C Vdc
	9500	MLSG952M010JK0C	0.096	0.091	6.9	7.1	15	1.5	12
10 Vdc @ 125 °C 12 Vdc @ 105 °C 15 Vdc Surge @ 25 °C	14000	MLSG143M010JA0C	0.068	0.064	9.8	10	15	2	12
	19000	MLSG193M010JH0C	0.053	0.050	12.6	12.9	15	2.5	12
	24000	MLSG243M010JB0C	0.042	0.040	15.4	15.8	15	3	12
	4600	MLSG462M020JK0C	0.102	0.097	6.6	6.8	30	1.5	24
20 Vdc @ 125 °C	6800	MLSG682M020JA0C	0.072	0.068	9.4	9.7	30	2	24
24 Vdc @ 105 °C 30 Vdc Surge @ 25 °C	9300	MLSG932M020JH0C	0.054	0.052	12.3	12.6	30	2.5	24
jiei	11000	MLSG113M020JB0C	0.042	0.040	15.2	15.6	30	3	24
	3300	MLSG332M030JK0C	0.103	0.098	6.6	6.8	45	1.5	36
30 Vdc @ 125 ℃ 36 Vdc @ 105 ℃ 45 Vdc Surge @ 25 ℃	4900	MLSG492M030JA0C	0.072	0.069	9.5	9.7	45	2	36
	6700	MLSG672M030JH0C	0.055	0.053	12.3	12.6	45	2.5	36
	8500	MLSG852M030JB0C	0.043	0.041	14.9	15.3	45	3	36
	2300	MLSG232M040JK0C	0.105	0.100	6.6	6.8	60	1.5	48
40 Vdc @ 125 °C 48 Vdc @ 105 °C 60 Vdc Surge @ 25 °C	3400	MLSG342M040JA0C	0.072	0.068	9.5	9.7	60	2	48
	4600	MLSG462M040JH0C	0.056	0.053	12.3	12.6	60	2.5	48
	5900	MLSG592M040JB0C	0.045	0.043	14.9	15.3	60	3	48
	1600	MLSG162M050JK0C	0.108	0.101	6.6	6.8	75	1.5	60
50 Vdc @ 125 °C 60 Vdc @ 105 °C 75 Vdc Surge @ 25 °C	2500	MLSG252M050JA0C	0.073	0.700	9.5	9.7	75	2	60
	3400	MLSG342M050JH0C	0.056	0.053	12.3	12.6	75	2.5	60
	4300	MLSG432M050JB0C	0.046	0.043	14.9	15.3	75	3	60
	1000	MLSG102M060JK0C	0.109	0.103	6.5	6.6	90	1.5	72
60 Vdc @ 125 °C 60 Vdc @ 105 °C 90 Vdc Surge @ 25 °C	1500	MLSG152M060JA0C	0.074	0.071	9.3	9.6	90	2	72
	2100	MLSG212M060JH0C	0.057	0.054	12.1	12.4	90	2.5	72
	2600	MLSG262M060JB0C	0.047	0.044	14.7	15	90	3	72
75 Vdc @ 125 °C 90 Vdc @ 105 °C 112 Vdc Surge @ 25 °C	790	MLSG791M075JK0C	0.246	0.234	4.0	4.2	112.5	1.5	90
	1100	MLSG112M075JA0C	0.200	0.190	5.0	5.2	112.5	2	90
	1500	MLSG152M075JH0C	0.148	0.141	6.2	6.5	112.5	2.5	90
	2000	MLSG202M075JB0C	0.096	0.091	8.2	8.5	112.5	3	90
	400	MLSG401M100JK0C	0.960	0.768	2	2.4	150	1.5	120
100 Vdc @ 125 °C 120 Vdc @ 105 °C 150 Vdc Surge @ 25 °C	600	MLSG601M100JA0C	0.634	0.507	2.8	3.6	150	2	120
	800	MLSG801M100JH0C	0.484	0.387	3.6	4.6	150	2.5	120
	1000	MLSG102M100JB0C	0.387	0.310	4.4	5.7	150	3	120
	200	MLSG201M150JK0C	0.960	0.768	2	2.4	225	1.5	180
150 Vdc @ 125 ℃ 180 Vdc @ 105 ℃ 225 Vdc Surge @ 25 ℃	300	MLSG301M150JA0C	0.634	0.507	2.8	3.6	225	2	180
	400	MLSG401M150JH0C	0.484	0.387	3.6	4.6	225	2.5	180
	500	MLSG501M150JB0C	0.387	0.310	4.4	5.7	225	3	180
	190	MLSG191M200JK0C	1.274	1.019	1.9	2.1	300	1.5	250
200 Vdc @ 125 °C 250 Vdc @ 105 °C 300 Vdc Surge @ 25 °C	280	MLSG281M200JA0C	0.845	0.676	2.8	3.1	300	2	250
	380	MLSG381M200JH0C	0.634	0.508	3.6	4.1	300	2.5	250
	490	MLSG491M200JB0C	0.507	0.406	4.4	5	300	3	250
	140	MLSG141M250JK0C	1.200	0.960	1.9	2.2	350	1.5	300
250 Vdc @ 125 °C	220	MLSG221M250JA0C	0.792	0.634	2.9	3.2	350	2	300
275 Vdc @ 105 °C 350 Vdc Surge @ 25 °C	300	MLSG301M250JH0C	0.605	0.484	3.7	4.2	350	2.5	300
550 vac surge @ 25 °C	380	MLSG381M250JB0C	0.484	0.387	4.5	5.1	350	3	300


Type MLSG – Slimpack[™], 5000 hr@125 °C, Aluminum Electrolytic


CDÉ

Typical Performance Curves

Part # MLSG122M060JKOC










Type MLSG – Slimpack™, 5000 hr@125 °C, Aluminum Electrolytic

Typical Performance Curves







Notice and Disclaimer: All product drawings, descriptions, specifications, statements, information and data (collectively, the "Information") in this datasheet or other publication are subject to change. The customer is responsible for checking, confirming and verifying the extent to which the Information contained in this datasheet or other publication is applicable to an order at the time the order is placed. All Information given herein is believed to be accurate and reliable, but it is presented without any guarantee, warranty, representation or responsibility of any kind, expressed or implied. Statements of suitability for certain applications are based on the knowledge that the Cornell Dubilier company providing such statements ("Cornell Dubilier") has of operating conditions that such Cornell Dubilier company regards as typical for such applications, but are not intended to constitute any guarantee, warranty or representation regarding any such matter – and Cornell Dubilier specifically and expressly disclaims any guarantee, warranty or representation concerning the suitability for a specific customer application, use, storage, transportation, or operating environment. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by Cornell Dubilier with reference to the use of any Cornell Dubilier products is given gratis (unless otherwise specified by Cornell Dubilier), and Cornell Dubilier assumes no obligation or liability for the advice given or results obtained. Although Cornell Dubilier strives to apply the most stringent quality and safety standards regarding the design and manufacturing of its products, in light of the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies or other appropriate protective measures) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage. Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicated in such warnings, cautions and notes, or that other safety measures may not be required.